

FIBROL PETROLEUM HT LCX-2 460 GREASE

NLGI GRADE	HT LCX-2 460
Colour	Golden Yellowish
Thickener	Lithium - Complex
Drop Point, , °C min	280
Worked Penetration	265 – 295
Operating Range , °C	-20 to 180 (300 F)
Viscosity at 40, °C cSt	460
Water wash out	1% max
4-Ball Weld Load	620 - 800



FIBROL PETROLEUM

Website: www.fibrolpetroleum.com Email: fibrolpetroleum@gmail.com, CONTACT Number: 9890140990