

FIBROL PETROLEUM FP HTXX 400 & 800 GREASE

TYPICAL PROPERTIES

PROPERTIES	FP HTXX 400	FP HTXX 800
NLGI grade	2	2
Thickener Type	Calcium Sulfonate Complex	Calcium Sulfonate Complex
Colour	Brown	Brown
Appearance	Smooth buttery	Smooth tacky
Penetration, Worked, 25 C	280	280
Dropping Point, C	+320	+320
Viscosity of Oil cSt @ 40 C	Mineral oil 220 cst	Mineral oil 460 cst
4-Ball Weld Test, Weld Point Kg	+400	+800
Water Washout	0.8 max	0.5 max
Operating Temperature	20°C to 250°C (360 F)	20°C to 280°C (400 F)



FIBROL PETROLEUM

Website: www.fibrolpetroleum.com Email: fibrolpetroleum@gmail.com, CONTACT Number: 9890140990